

## Molten Salt Heat Transfer Fluid

### Process Applications

- Very high-temperature applications
- Solar thermal storage
- Hot bath systems
- High-temperature reaction applications
- Preheating natural gas lines
- Metal alloy heat treatments
- Environmental chambers

### ■ Dynalene MS-2 Overview

Dynalene MS-2 is a non-toxic molten salt heat transfer fluid which can be used in hot bath or solar thermal applications at very high temperatures. MS-2 can safely withstand temperatures up to 485°C, higher than most commercially available heat transfer fluids on the market today. Dynalene MS-2 has a lower melting point than MS-1, providing extra freeze protection and a wider operating range.

Dynalene's molten salt fluids have excellent thermo-physical properties in the liquid state, such as low viscosity, high heat capacity, and high thermal conductivity. The high energy density of Dynalene's molten salts provides long-term heat storage for any high-temperature application. Our heat transfer salts provide excellent corrosion resistance to stainless and alloy steels and exhibit minimal vapor pressures even near peak operating temperatures. This eliminates the need for expensive materials and high pressure components, in addition to increasing the safety of your system.

### ■ Thermal Stability

The maximum operating temperature of MS-2 is 485°C. Above this temperature the fluid will slowly evolve into non-toxic, inert gases with very low vapor pressures. Prolonged exposure to temperatures higher than the recommended maximum operating temperature may lead to solidification in the melt.

### ■ Corrosion Performance

Dynalene MS-2 has undergone repeated corrosion testing with stainless steels for extended periods of time. Stainless steel samples were tested and analyzed for mass loss over 36 days in an atmosphere with an oxygen partial pressure of .21 atm at 550°C. The corrosion rates for SS-304 and SS-316 were determined to be 24 µm/yr and 21 µm/yr, respectively.

### Recommended Temperature Range:

140°C (284°F) to 485°C (905°F)

### ■ Properties of Dynalene MS-2

A comprehensive list of all thermo-physical properties of Dynalene MS-2 can be found on page 2. For health and safety information or to request a Material Safety Data Sheet, contact our Dynalene sales representatives.

Composition:	Molten salt mixture
Appearance:	White solids
Odor:	None
Freezing Point:	130°C (266°F)
Max Operating Temp:	485°C (905°F)
Latent Heat:	135 J/g
Thermal Conductivity*:	0.50 W/mK
Specific Heat*:	1.59 J/gK
Density*:	1.89 g/cm <sup>3</sup>
Viscosity*:	4.0 cP
Freezing Contraction:	3%

*\*Taken at 300°C*

### ■ Benefits of Choosing Dynalene MS-2

- Non-toxic
- High thermal stability
- High energy density
- Low vapor pressure
- Cost-effective
- Available throughout North America
- Total fluid care
- Proven performance

## SI Units

Temp °C	Viscosity mPa·s	Thermal Cond. W/m·K	Specific Heat kJ/kg·K	Density kg/m <sup>3</sup>
150	20		1.58	2000
200	10		1.58	1960
250	5.9	0.49	1.59	1930
300	4.0	0.50	1.59	1890
350	2.8	0.51	1.59	1860
400	2.1	0.52	1.59	1820
450	1.7	0.53	1.60	1790
500	1.5	0.54	1.60	1760

## US Units

Temp °F	Viscosity cP	Thermal Cond. BTU/hr·ft·°F	Specific Heat BTU/lb·°F	Density lb/ft <sup>3</sup>
302			0.38	125
392			0.38	122
482	5.9	0.28	0.38	120
572	4.0	0.29	0.38	118
662	3.1	0.29	0.38	116
752	2.4	0.30	0.38	114
842	1.9	0.31	0.38	112
932	1.7	0.31	0.38	110