

Ternary Molten Salt Heat Transfer Fluid

Process Applications

- Solar heat transfer fluid
- Solar thermal storage
- Environmental chambers
- Hot bath systems
- High-temperature reaction applications
- Preheating natural gas lines
- Metal alloy heat treatments

■ Dynalene MS-450 Overview

Dynalene MS-450 is a safe-to-use molten salt heat transfer fluid which can be used in hot bath or solar thermal applications. It can safely withstand temperatures up to 450°C. Dynalene MS-450 has a lower melting point than other commercially available molten salts, providing extra freeze protection.

Dynalene's molten salt fluids have excellent thermo-physical properties in the liquid state, such as low viscosity, high heat capacity, and high thermal conductivity. The high energy density of Dynalene's molten salts provides long-term heat storage for any high-temperature application. Our heat transfer salts provide excellent corrosion resistance with stainless and alloy steels, and exhibit minimal vapor pressures even near peak operating temperatures. This eliminates the need for expensive materials and high-pressure components, in addition to increasing the safety of your system.

MS-450 is expected to give off water vapor during the initial heating, so be sure the system is vented to the atmosphere to allow all the vapor to escape.

■ Thermal Stability

The maximum operating temperature of MS-450 is 450°C. Above this temperature the fluid will slowly evolve into gases of nitrogen with very low vapor pressures. Prolonged exposure to temperatures higher than the recommended maximum operating temperature may lead to precipitate formation.

■ Material Compatibility

Dynalene MS-450 can be used safely with stainless steels, Inconel, iron aluminides, nickel aluminides, and most alloy steel up to 450°C. Copper and bronze can be used up to 300°C, and carbon steel up to 400°C.

Recommended Temperature Range:

150°C (302°F) to 450°C (842°F)

■ Properties of Dynalene MS-450

A comprehensive list of all thermo-physical properties of Dynalene MS-450 can be found on page 2. For health and safety information or to request a Safety Data Sheet, contact our Dynalene sales representatives.

Composition:	Salt mixture
Appearance:	Off-white, translucent solids
Odor:	None
Melting Point:	120°C (248°F)
Max Operating Temp:	450°C (842°F)
Latent Heat:	95 J/g
Thermal Conductivity*:	0.473 W/mK
Specific Heat*:	1.26 J/gK
Density*:	1.92 g/cm ³
Viscosity*:	11.7 cP
Freezing Contraction:	5%

*Measured at 300°C (572°F)

■ Benefits of Choosing Dynalene MS-450

- Safe-to-use
- High thermal stability
- High energy density
- Low vapor pressure
- Cost-effective
- Available worldwide
- Proven performance

■ Quantity & Availability

Dynalene MS products are offered in 16, 50, 220, and 550-lb containers, and 2000 to 3000-lb super sacks. Pricing depends on quantity, and Dynalene, Inc. will work with you to try to fit your budget.

Properties of Dynalene MS-450

SI Units

Temp °C	Viscosity mPa·s	Thermal Cond. W/m·K	Specific Heat kJ/kg·K	Density kg/m ³
130	1089	0.435	1.252	2035
135	666	0.436	1.252	2031
140	436	0.437	1.252	2028
145	302	0.438	1.253	2025
150	220	0.439	1.253	2022
155	167	0.440	1.253	2018
160	131	0.441	1.253	2015
165	106	0.443	1.254	2012
170	88.1	0.444	1.254	2008
175	74.6	0.445	1.254	2005
180	64.3	0.446	1.254	2002
185	56.1	0.447	1.255	1999
190	49.7	0.448	1.255	1995
195	44.4	0.449	1.255	1992
200	40.0	0.450	1.255	1989
220	28.2	0.455	1.256	1976
240	23.2	0.459	1.257	1963
260	17.8	0.464	1.258	1949
280	14.2	0.468	1.259	1936
300	11.7	0.473	1.260	1923
320	9.8	0.477	1.261	1910
340	8.5	0.481	1.262	1897
360	7.5	0.486	1.263	1884
380	6.7	0.490	1.264	1871
400	6.0	0.495	1.265	1858
420	5.5	0.499	1.266	1844
440	5.1	0.504	1.267	1831
460	4.7	0.508	1.268	1818

US Units

Temp °F	Viscosity cP	Thermal Cond. BTU/hr·ft·°F	Specific Heat BTU/lb·°F	Density lb/ft ³
266	1089	0.251	0.299	127.2
275	666	0.252	0.299	127.0
284	436	0.253	0.299	126.8
293	302	0.253	0.299	126.6
302	220	0.254	0.299	126.4
311	167	0.255	0.299	126.1
320	131	0.255	0.299	125.9
329	106	0.256	0.299	125.7
338	88.1	0.256	0.300	125.5
347	74.6	0.257	0.300	125.3
356	64.3	0.258	0.300	125.1
365	56.1	0.258	0.300	124.9
374	49.7	0.259	0.300	124.7
383	44.4	0.260	0.300	124.5
392	40.0	0.260	0.300	124.3
428	28.2	0.263	0.300	123.5
464	23.2	0.265	0.300	122.7
500	17.8	0.268	0.301	121.8
536	14.2	0.271	0.301	121.0
572	11.7	0.273	0.301	120.2
608	9.8	0.276	0.301	119.4
644	8.5	0.278	0.301	118.6
680	7.5	0.281	0.302	117.7
716	6.7	0.283	0.302	116.9
752	6.0	0.286	0.302	116.1
788	5.5	0.289	0.302	115.3
824	5.1	0.291	0.303	114.5
860	4.7	0.294	0.303	113.6

US to SI Conversions:

Viscosity: 1 cP = 0.001 Pa·s

Thermal Cond.: 1 Btu/hr·ft·°F = 1.73 W/mK

Specific Heat: 1 Btu/lb_m·°F = 4,186 J/kg°C

Density: 1 lb_m/ft³ = 16 kg/m³

Product Disclaimer

The information contained in this entire publication is presented in good faith at “no charge” and is believed to be correct as of the date indicated. No representations or warranties are made as to its completeness or accuracy. The information listed is supplied upon the condition that the persons receiving it will make their own determination as to its suitability for their purposes prior to use. In no event will the seller be responsible for damages of any nature whatsoever resulting from the use of, or reliance upon, this information or the product to which this information refers. Nothing contained on this page is to be construed as a recommendation to use the product, process, equipment or formulation in conflict with any patent. No representation or warranty, expressed or implied, is made that the use of this product will not infringe any patent.

No representations or warranties, either expressed or implies, of merchantability, fitness for a particular purpose or for any other nature are made with respect to the information, or the product to which the information refers.

Contact Information

Corporate Headquarters

Dynalene, Inc.
5250 West Coplay Road
Whitehall, Pennsylvania 18052
Phone: 610-262-9686 / 1-877-244-5525
Fax: 610-262-7437
Email: info@dynalene.com
Website: www.dynalene.com

Midwest Location

248 Beinoris Dr
Wood Dale, IL 60191
Phone: 1-855-216-7639
Email: centralsales@dynalene.com

West Location

1701 S 5350 W
Salt Lake City, UT 84104
Phone: 1-877-244-5525
Email: westsales@dynalene.com