

Molten Salt Heat Transfer Fluid

Process Applications

- Solar heat transfer fluid
- Thermal storage medium
- Environmental chambers
- Hot bath systems
- High-temperature reaction applications
- Preheating natural gas lines
- Metal alloy heat treatments

■ Dynalene MS-2 Overview

Dynalene MS-2 is a non-toxic molten salt heat transfer fluid which can be used in hot bath or solar thermal applications at very high temperatures. It can safely withstand temperatures up to 485°C. Dynalene MS-2 has a lower melting point than other commercially available molten salts, providing extra freeze protection.

Dynalene's molten salt fluids have excellent thermo-physical properties in the liquid state, such as low viscosity, high heat capacity, and high thermal conductivity. The high energy density of Dynalene's molten salts provides long-term heat storage for any high-temperature application. Our heat transfer salts provide excellent corrosion resistance to stainless and alloy steels, and exhibit minimal vapor pressures even near peak operating temperatures. This eliminates the need for expensive materials and high-pressure components, in addition to increasing the safety of your system.

■ Thermal Stability

The maximum operating temperature of MS-2 is 485°C. Above this temperature the fluid will slowly evolve into non-toxic, inert gases with very low vapor pressures. Prolonged exposure to temperatures higher than the recommended maximum operating temperature may lead to precipitate formation.

■ Corrosion Performance

Dynalene MS-2 has undergone repeated corrosion testing with stainless steels for extended periods of time. Stainless steel samples were tested and analyzed for mass loss over 36 days in an atmosphere with an oxygen partial pressure of 0.21 atm at 550°C. The corrosion rates for SS-304 and SS-316 were determined to be 24 µm/year and 21 µm/year, respectively.

■ Material Compatibility

Dynalene MS-2 can be used safely with carbon steel up to 400°C (752°F). Above this operating temperature, stainless steel, Inconel, or other corrosion-resistant alloys are recommended. Copper and bronze can be used up to 300°C (572°F).

Recommended Temperature Range:

140°C (284°F) to 485°C (905°F)

■ Properties of Dynalene MS-2

A comprehensive list of all thermo-physical properties of Dynalene MS-2 can be found on page 2. For health and safety information or to request a Safety Data Sheet, contact our Dynalene sales representatives.

Composition:	Salt mixture
Appearance:	White solids
Odor:	None
Melting Point:	130°C (266°F)
Max Operating Temp:	485°C (905°F)
Latent Heat:	135 J/g
Thermal Conductivity*:	0.50 W/mK
Specific Heat*:	1.59 J/gK
Density*:	1.89 g/cm ³
Viscosity*:	4.0 cP
Freezing Contraction:	3%

*Taken at 300°C/572°F

■ Benefits of Choosing Dynalene MS-2

- Non-toxic
- High thermal stability
- High energy density
- Cost-effective
- Low vapor pressure
- Cost-effective
- Available worldwide
- Proven performance

■ Quantity and Availability

Dynalene MS products are offered in 16, 50, 220, and 550-lb containers, and 2000 to 3000-lb super sacks. Pricing depends on quantity, and Dynalene, Inc. will work with you to try to fit your budget.

SI Units

Temp °C	Viscosity mPa·s	Thermal Cond. W/m·K	Specific Heat kJ/kg·K	Density kg/m ³
150	20		1.58	2000
200	10		1.58	1960
250	5.9	0.49	1.59	1930
300	4.0	0.50	1.59	1890
350	2.8	0.51	1.59	1860
400	2.1	0.52	1.59	1820
450	1.7	0.53	1.60	1790
500	1.5	0.54	1.60	1760

US Units

Temp °F	Viscosity cP	Thermal Cond. BTU/hr·ft·°F	Specific Heat BTU/lb·°F	Density lb/ft ³
302			0.38	125
392			0.38	122
482	5.9	0.28	0.38	120
572	4.0	0.29	0.38	118
662	3.1	0.29	0.38	116
752	2.4	0.30	0.38	114
842	1.9	0.31	0.38	112
932	1.7	0.31	0.38	110

Product Disclaimer

The information contained in this entire publication is presented in good faith at “no charge” and is believed to be correct as of the date indicated. No representations or warranties are made as to its completeness or accuracy. The information listed is supplied upon the condition that the persons receiving it will make their own determination as to its suitability for their purposes prior to use. In no event will the seller be responsible for damages of any nature whatsoever resulting from the use of, or reliance upon, this information or the product to which this information refers. Nothing contained on this page is to be construed as a recommendation to use the product, process, equipment or formulation in conflict with any patent. No representation or warranty, expressed or implied, is made that the use of this product will not infringe any patent.

No representations or warranties, either expressed or implied, of merchantability, fitness for a particular purpose or for any other nature are made with respect to the information, or the product to which the information refers.

Contact Information

Corporate Headquarters

Dynalene, Inc.
5250 West Coplay Road
Whitehall, Pennsylvania 18052
Phone: 610-262-9686 / 1-877-244-5525
Fax: 610-262-7437
Email: info@dynalene.com
Website: www.dynalene.com

Midwest Location

248 Beinoris Dr
Wood Dale, IL 60191
Phone: 1-855-216-7639
Email: centeralsales@dynalene.com

West Location

1701 S 5350 W
Salt Lake City, UT 84104
Phone: 1-877-244-5525
Email: westsales@dynalene.com

Published August 2020